



DATA SHEET

Filter media

Dryflo®

Dryflo®

Appearance	White, corrugated
Use	Pleated filter media for use in cartridges
Composition	Synthetic/glass-fibre filter media
Area weight	140 g/m ²
Thickness	0.69 mm
Air Permeability (Frazier)	580 m ³ /m ² .h at 125 Pa
IFA/BIA certificate (DIN 660335-2-69)	N/A
Temperature (dry heat)	
Continuous	65 °C
Peaks	80 °C
Chemical resistance	
Hydrolysis	Poor
Acids	Good
Alkalis	Good
Oxidising agents	Good
Organic solvents	Good
Abrasion resistance	Poor
Supports combustion	Yes
Application field	Excellent performance on water soluble straight oils, semi-synthetic and synthetic coolants. Typical applications include wet machining, metalworking, drilling, cutting, etc.